

# BITUTAK<sup>®</sup> COLD<sup>®</sup> BY SOPREMA<sup>®</sup> Mineral

PD10001-REV. 21154

## PRODUCT DESCRIPTION

BITUTAK<sup>®</sup> Cold Mineral is a 4.0 mm (157 mils) APP (Atactic Polypropylene) modified bitumen roofing membrane for approved multi-ply membrane and flashing assemblies. BITUTAK's exclusive APP polymer and asphalt formulation yield excellent weathering characteristics and long-term durability. Reinforced with a heat-resistant, non-woven polyester mat provides added strength and puncture resistance to the membrane. BITUTAK<sup>®</sup> Cold Mineral is available in standard black or white mineral surface. For your next roofing project, discover how BITUTAK<sup>®</sup> delivers exceptional waterproofing performance at a fantastic value.



## PHYSICAL PROPERTIES

PROPERTY / UNIT	MD	XMD	ASTM TEST METHOD
Peak Load @ 0°F (-18°C); lbf/in (kN/m)	145 (25.4)	105 (18.4)	D5147
Elongation at Peak Load @ 0°F (-18°C); %	30	25	D5147
Peak Load @ 73.4°F (23°C); lbf/in (kN/m)	110 (19.3)	75 (13.1)	D5147
Elongation at Peak Load @ 73.4°F (23°C); %	45	45	D5147
Tear Strength @ 73.4°F (23°C); lbf (N)	150 (667)	115 (512)	D5147
Dimensional Stability; %	< 0.5	< 0.5	D5147
Low Temperature Flexibility; °F (°C)	3 (-16)	3 (-16)	D5147
Compound Stability; °F (°C)	> 275 (135)	> 275 (135)	D5147
Granule Embedment; g	< 2.0		D5147

All values shown are nominal and subject to normal manufacturing tolerances.

## PRODUCT INFORMATION

ASTM STANDARD	LENGTH (ft)	WIDTH (in)	THICKNESS (mils)	WEIGHT (lb)	COVERAGE (sq ft)
D6222 Type I, Grade G	32.8 (10.0 m)	39.4 (1.0 m)	157 (4.0 mm)	105 (47.6 kg)	97.9 (9.1 sq m)

## INSTALLATION

<b>Surface Preparation</b>	The substrate should be clean, stable, dry, free of any loose materials, grease, and other contaminants, which may compromise the product's performance.
<b>Minimum Installation Temperature</b>	40°F (4°C)
<b>Installation</b>	Install the membrane using cold-applied adhesive or heat welded. When installed with an adhesive, all side and end laps need to be fully heat welded. Side laps must be a minimum of 3 inches (76 mm) and end laps a minimum of 6 inches (152 mm).
<b>Recommendations/Restrictions</b>	When heat welding on combustible substrates (wood, plywood, and OSB), a protective coverboard must be installed before application. Keep any combustible material away from an open flame.

## FIRE SAFETY GUIDELINES

Torch application of BITUTAK<sup>®</sup> Cold Mineral may threaten fire if strict application standards and procedures are not followed. All operators of torch equipment should be thoroughly trained. In addition, a fire watch should be maintained on the project for no less than 60 minutes following the last heat-welded work of the day. An ABC-approved fire extinguisher should be on the site for each torch in operation.

## PACKAGING & STORAGE

Each pallet contains 20 rolls. Rolls should be stored on end, on raised platforms, and protected from the weather.



www.soprema.us  
310 Quadral Drive, Wadsworth, Ohio 44281  
TOLL FREE: (800)356-3521 | TEL: (800)334-0066

